INTEGRATED IAM

SERVICES

**INSIDE DELPHION** 

**Q-Q-1**O- --

(I) 1000-0000 (II) -()-()-(-111)

153

Lig. crystal mixt. used as matrix for ferroelectric lig. crystal - contains 2 5-alkoxy-2-(4-alkoxyphenyl)pyrimidine cpds.

Assignee:

**HOECHST AG** Standard company (FARH...)

Inventor:

DUBAL H R; DUEBAL H; ESCHER C; HEMMERLING W; MUELLER I; MULLER I;

**OHLENDORF D; WINGEN R;** 

Accession / Update:

1989-087286 / 198912

IPC Code:

C09K 19/34; G02F 1/13;

**Derwent Classes:** 

E13; L03; P81; U11; V07;

Manual Codes:

E07-D12(Pyrimidine), L03-D01D2(Liquid crystal material mixtures), U11-A03(Liquid

crystal, electrochromic materials), V07-K(Controlling light)

**Derwent Abstract** 

**RECORD** 

(EP0307880A) Liquid crystal mixt. contains at least two 5-alkoxy-2-(4-alkoxy-phenyl)-

pyrimidines, with linear alkyl gps., of formula (I), where n = 6-14; x = 2-14. In the mixt., n is constant and pref. = 7-14; and the values of x differ by at least 2.

**DERWENT** The mixt. pref. contains 20-90 (mole-)% (i) and pref. also 2-40%

cyclohexanecarboxylate ester(s) of formula (II), 10-35% alkenyloxy-phenyl-pyrimidine deriv(s). of formula (III) and/or 10-25% alkyl-pyrimidine-alkoxy-phenyl deriv(s). of

formula (IV). In the formulae R1 = 10-16C alkyl or 7-14C alkoxy; R2 = 2-9C alkyl; R3

= 7-16C alkyl or 6-14C alkoxy; y = 4-14; m and p independently = 6-14. USE/Advantage - The mixts. are claimed for use as matrix for ferroelectric liquid crystal mixts., which also contain an optically active dopant and in electro-optical devices. They have favourable optical and dielectric anisotropy and a wide enough nematic phase for practical applications, esp. a low m.pt. low transition point of the lower limit of the SC phase and a much wider SC phase than that obtd. using the corresp. 5-alkyl-2-(4-alkoxy- phenyl) pyrimidine cpds.. They can give ferroelectric liquid crystal mixts, with short switching time with the phase sequence isotropic to nematic to smectic A, smectic C in which the pitch in the nematic phase is over 15

microns and in the S asterisk c phase over 5 microns, with a negative dielectric anisotropy and optical anisotropy less than 0.15.

Abstract info:

EP0307880A: Dwg.0/0, EP0307880B: Dwg.0/0, US5071589:

Images:

Family:

**Patent** Pub. Date DW Update Pages Language **IPC Code** EP0307880A \* March 22, 1989 198912 German C09K 19/34

Des. States: (R) AT BE CH DE FR GB IT LI NL SE

Local appls.: EP1988000115003 ApplDate:1988-09-14 (88EP-0115003)

DE3887048G = Feb. 24, 1994 199409 German C09K 19/34

Local appls.: Based on EP00307880 (EP 307880)

EP1988000115003 ApplDate:1988-09-14 (88EP-0115003)

DE1988003887048 ApplDate:1988-09-14 (88DE-3887048)

Jan. 12, 1994 EP0307880B1 = 199403 C09K 19/34

Des. States: (R) AT BE CH DE FR GB IT LI NL SE

Local appls.: EP1988000115003 ApplDate:1988-09-14 (88EP-0115003)

US5071589 = Dec. 10, 1991 199201 11 C09K 19/34

Local appls.: <u>US1988000245408</u> ApplDate:1988-09-16 (88US-0245408)

198921 C02F 3/00 April 14, 1989 English JP1096285A = Local appls.: JP1988000230221 ApplDate:1988-09-16 (88JP-0230221) 198920 NO\_NO NO8804137A = April 10, 1989 Local appls.: March 30, 1989 198914 C09K 19/34 DE3831226A = German Local appls.: DE1988003831226 ApplDate:1988-09-14 (88DE-3831226)

Priority Number:

A

Application Number	Application Date	Original Title
DE1987003731640	Sept. 19, 1987	

Citations:

<u>EP0293910</u>: LIQUID CRYSTAL COMPOSITION AND LIQUID CRYSTAL DEVICE CONTAINING SAME <u>EP0308794</u>: LIQUID CRYSTAL PHENYL PYRIMIDINE ESTER OF CYCLOHEXANE-CARBOXYLIC ACID WITH A SMECTIC PHASE, PROCESS FOR ITS PREPARATION AND ITS USE IN LIQUID CRYSTAL MIXTURES <u>WO8604060</u>: PYRIMIDINES

- A3...199012 - No-SR.Pub

Related Accessions:

Accession Number	Туре	Derwent Update	Derwent Title
C1989-038598	С		
N1989-066582	N		
2 items found			

Title Terms:

LIQUID CRYSTAL MIXTURE MATRIX FERROELECTRIC LIQUID CRYSTAL CONTAIN ALKOXY ALKOXYPHENYL PYRIMIDINE COMPOUND

Index Terms:

**ALKOXYPHENYL** 



Data copyright Derwent 2002

Derwent Searches Patent / Accession

Numbers

<u>Boolean Text</u>

Advanced Text

Demo area...

© 1997-2002 Delphion, Inc.

Research Subscriptions | Privacy Policy | Terms & Conditions | Site Map | Contact Us